

NISHIDA, Takanobu
Serial No. 09/986,987

Atty Dkt: 900-407
Art Unit: 1763

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) An ashing method comprising the steps of:
holding a substrate having a resist mask formed on a low dielectric constant insulating film in a chamber of an ashing apparatus;
| applying an RF electric power to activate an almostsubstantially pure oxygen gas introduced in the chamber in order to perform ashing of the resist mask, while an RF electric power is applied to the substrate, thereby obtaining formation of a protective film on a surface of the low dielectric constant insulating film;
wherein a ratio (W_s/W_b) of the RF electric power (W_s) for activating the
| almostsubstantially pure oxygen gas to the RF electric power (W_b) applied to the substrate is set so that the change rate of the dielectric constant of the low dielectric constant insulating film before and after ashing is 10 % or less; and
wherein the ratio (W_s/W_b) is controlled to be 5 or less.
2. (Original) The ashing method according to claim 1, wherein the RF electric power (W_b) applied to the substrate is controlled to be a predetermined value or higher.
3. (Original) The ashing method according to claim 2, wherein the RF electric power (W_b) is 150 W or higher.
4. (Currently Amended) The ashing method according to claim 1, wherein the RF
| electric power (W_s) for activating the almostsubstantially pure oxygen gas is 1000 W or less.

NISHIDA, Takanobu
Serial No. 09/986,987

Atty Dkt: 900-407
Art Unit: 1763

5. (CANCELLED)

6. (CANCELLED)

7. (CANCELLED)

8. (Original) The ashing method according to claim 1, wherein the substrate is set to a temperature of about 20°C or lower.

9. (Previously Presented) The ashing method according to claim 1, wherein the low dielectric constant insulating film formed on the substrate has a dielectric constant of 3.5 or less.

10. (Currently Amended) The ashing method according to claim 1, wherein the RF electric power applied for activation of the almost~~substantially~~ pure oxygen gas is supplied by a first power source and the RF electric power applied to the substrate is supplied by a second power source via a lower electrode formed in the chamber.

11. (Original) The ashing method according to claim 10, wherein the lower electrode supports the substrate and is controlled to have a predetermined temperature for maintaining the temperature of the substrate.

12. (CANCELLED)

13. (Currently Amended) An ashing method comprising the steps of:

(1) situating a substrate having a resist mask formed on a low dielectric constant insulating film in a chamber of an ashing apparatus;

(2) introducing an almost~~substantially~~ pure oxygen gas into the chamber;

NISHIDA, Takanobu
Serial No. 09/986,987

Atty Dkt: 900-407
Art Unit: 1763

(3) applying an RF electric power to activate the almost substantially pure oxygen gas;

(4) applying RF electric power to the substrate while performing step (3);

wherein steps (2) - (4) result in formation of a protective film on a surface of the low dielectric constant insulating film and are performed in a manner substantially to avoid bonding that would substantially change a dielectric constant of the low dielectric constant insulating film; and

wherein a ratio (W_s/W_b) of the RF electric power (W_s) for activating the substantially almost pure oxygen gas to the RF electric power (W_b) applied to the substrate is controlled to be 5 or less and so that the change rate of the dielectric constant of the low dielectric constant insulating film before and after ashing is 10 % or less.

14. (Previously Presented) The ashing method according to claim 13, wherein steps (2) - (4) are performed in a manner substantially to avoid at least one of Si-H bonding and H-OH bonding with the low dielectric constant insulating film.

15. (CANCELED)

16. (Previously Presented) The ashing method according to claim 13, wherein steps (2) - (4) are performed in a manner so that a rate of change of the dielectric constant of the low dielectric constant insulating film is less than about 10% when the RF electric power applied to the substrate in step (4) is at least about 150 W.

17. (Previously Presented) The ashing method according to claim 13, wherein steps (2) - (4) are performed in a manner so that a rate of change of the dielectric constant of the low dielectric constant insulating film is less than about 8% when the RF electric power applied to the substrate in step (4) is at least about 190 W.

NISHIDA, Takanobu
Serial No. 09/986,987

Atty Dkt: 900-407
Art Unit: 1763

18. (Previously Presented) The ashing method according to claim 13, wherein steps (2) - (4) are performed in a manner so that a rate of change of the dielectric constant of the low dielectric constant insulating film is less than about 5% when the RF electric power applied to the substrate in step (4) is at least about 250 W.

19. (Currently Amended) An ashing method comprising the steps of:
holding a substrate having a resist mask formed on a low dielectric constant insulating film in a chamber of an ashing apparatus;
applying an RF electric power to activate an almostsubstantially pure oxygen gas introduced in the chamber in order to perform ashing of the resist mask, while an RF electric power is applied to the substrate, thereby obtaining formation of a protective film on a surface of the low dielectric constant insulating film;

wherein the RF electric power (Ws) for activating the almostsubstantially pure oxygen gas is 1000 W or less; and

wherein a ratio (Ws/Wb) of the RF electric power (Ws) for activating the almostsubstantially pure oxygen gas to the RF electric power (Wb) applied to the substrate is controlled to be 5 or less and so that the change rate of the dielectric constant of the low dielectric constant insulating film before and after ashing is 10 % or less.

20. (CANCELLED)

21. (CANCELLED)

22. (Previously Presented) The ashing method according to claim 13, wherein the low dielectric constant insulating film has a dielectric constant of 3.5 or less.

NISHIDA, Takanobu
Serial No. 09/986,987

Atty Dkt: 900-407
Art Unit: 1763

23. (Previously Presented) The ashing method according to claim 19, wherein the low dielectric constant insulating film is a low dielectric constant film has a dielectric constant of 3.5 or less.